

NEVOSIL[®] MH 1500

Water Repellent for Construction Materials

Characteristics

Methyl hydrogen polysiloxane.

Application

NEVOSIL[®] MH 1500 is mainly used as a waterproofing agent for gypsum block production processes. Besides, it should be used in other processes such as textile, plaster, printing and dyeing with the same purpose of use.

Technical Data

Appearance	Clear liquid
Density (25°C)	~1,0 (g/ml)
Viscosity (25°C)	15-35 (cP)
Hydrogen content	1,49-1,55 (%)
Flashpoint	>120 (°C)

* These figures are only intended as a guide and should not be used in preparing specifications.

Processing

The recommended dosages should be changed, depending on the application area and purpose. This is why the proper required amount should be determined by making preliminary trials before the application.

Storage / Shelf Life

NEVOSIL[®] MH 1500 has a shelf life up to 9 months if stored in tightly closed original containers between 5-35°C. If the material is kept beyond the shelf life recommended, it is not necessarily unusable, but quality control should be performed on the properties relevant to the application. The containers must be protected against sunlight and frost.

Packaging

30, 60, 120 and 200 kgs plastic drums or 1,000 kgs IBC containers.

The data presented in this leaflet are in accordance with the present state of our knowledge, but do not absolve the user from carefully checking all supplies immediately on receipt. We reserve the right to alter product constants with the scope of technical progress or new developments. The recommendations made in this leaflet should be checked by preliminary trials.

Editing Date: 07.03.13
Revision No/Date: -
Page: 1/1

Ultrakim Kimya San. ve Tic. A.S.
Haramidere Sanayi Sitesi M Blok
No: 322-324 Avcilar, 34840, Istanbul/Turkey
Tel: + 90 212 422 05 14
Fax: + 90 212 422 05 15
Email: info@ultrakim.com

www.ultrakim.com