

NEVOSOFT® RA 4040-2 macro

Textile Softener

Characteristics

Non-ionic, amino functional polydimethylsiloxane emulsion.

Properties

- ✓ Provides very special softness to the fabric
- ✓ Yields slippery filled and permanent hand
- ✓ Ensures excellent sewability

Application

NEVOSOFT® RA 4040-2 macro is ideal as a permanent softener and lubricant for all kind of textile fabrics. Due to its reactive structure, it provides especially soft, slippery and filled elastomeric touch to the fabrics. Besides, it helps to improve the sewability.

Technical Data

Appearance	White liquid
Solid content (105°C-1h) (%)	40 (±1)
Emulsifier type	Non-ionic
pH	5,0-7,0

* These figures are only intended as a guide and should not be used in preparing specifications.

Processing

NEVOSOFT® RA 4040-2 macro can be applied by padding method. The finishing liquors should not be subjected to high shear, as this might cause instability. It is important to keep controlling the bath pH between 5,0-6,0 and the bath temperature below 40°C during the process. It is recommended to use 5-30 g/l of NEVOSOFT® RA 4040-2 macro for padding. The recommended fixing time and temperature is 1-3 min and 130-165°C, respectively.

NEVOSOFT® RA 4040-2 macro could be combined with all conventional cationic, nonionic softeners and other additives. However, the compatibility tests should be done before the application. Due to the cationic structure of its active material, NEVOSOFT® RA 4040-2 macro cannot be used together with anionic auxiliary substances.

The data presented in this leaflet are in accordance with the present state of our knowledge, but do not absolve the user from carefully checking all supplies immediately on receipt. We reserve the right to alter product constants with the scope of technical progress or new developments. The recommendations made in this leaflet should be checked by preliminary trials.

NEVOSOFT® RA 4040-2 macro

Textile Softener

Storage / Shelf Life

NEVOSOFT® RA 4040-2 macro has a shelf life up to 9 months if stored in tightly closed original containers between 5-35°C. If the material is kept beyond the shelf life recommended, it is not necessarily unusable, but quality control should be performed on the properties relevant to the application. The containers must be protected against sunlight and frost.

Packaging

30, 60, 120 and 220 kgs plastic drums or 1,000 kgs IBC containers.

Technical
Data
Sheet

NEVOSOFT®

The data presented in this leaflet are in accordance with the present state of our knowledge, but do not absolve the user from carefully checking all supplies immediately on receipt. We reserve the right to alter product constants with the scope of technical progress or new developments. The recommendations made in this leaflet should be checked by preliminary trials.